

AEROSOL® TR-70 surfactant

Type: Anionic

Chemical: Sodium Bistridecyl Sulfosuccinate

CAS No.: 2673-22-5

Molecular Formula: C₃₀H₅₇O₇NaS

Molecular Weight: 584

AEROSOL TR-70 surfactant is an extremely hydrophobic surface active agent with excellent solubility in organic media, and very low critical micelle concentration and equilibrium surface tension. It is extremely effective as a dispersant for resins, pigments, inks and dyes in organic systems. It is particularly effective in flushing pigments from aqueous press cakes to solvent media, and in imparting oleophilic properties to hydrophilic pigments and resins. It is also effective as an emulsifier in the emulsion polymerization of vinyl chloride and vinyl acetate, and in the suspension polymerization of vinyl chloride.

Surface Active Properties

Critical Micelle Concentration

(CMC) % by weight 0.001

Surface tension, 25°C

Concentration % by weight	dynes/cm
0.0001	70.0
0.0005	38.8
0.001	35.8
0.003	32.7
0.025	27.9
0.05	27.5
0.1	26.9

Interfacial tension, dynes/cm,

25°C, 1% solution

vs. organic liquid,

DuNouy Method, dynes/cm

Mineral oil 4.0

Toluene 7.5

Ross Miles Foam Test

ASTM D-1173,

0.1% solution, 50°C

Initial foam volume, mL 25.0

Foam volume after

21 minutes, mL -0.0

Representative Applications

AEROSOL TR-70 surfactant is very effective in applications where a high degree of organic solubility is required.

Emulsion and suspension polymerization, especially of vinyl chloride monomer. Suspensions of any desired particle size in the range of 1-10 microns can be prepared using AEROSOL TR-70 surfactant with a protective colloid of appropriate molecular weight. The polymer produced has good dielectric properties and heat stability.

Printing ink applications - When added to a printing ink with an organic base such as mineral oil, AEROSOL TR-70 surfactant produces an excellent dispersion with good plastic viscosity, yield value, texture and thixotropy. A hydrophilic pigment can also be made oleophilic by using AEROSOL TR-70 surfactant either sprayed on the pigment or added to the organic base.

Rust-preventive applications - AEROSOL TR-70 surfactant can be combined with other materials, such as petrolatum, lanolin and kerosene, to produce excellent rustpreventive formulations.

Non-aqueous pigment dispersions -

AEROSOL TR-70 surfactant is an excellent dispersing agent for organic and inorganic materials in organic systems. When used with pigments, it produces dispersions with excellent stability, rheological properties and opacity.

Physical and Chemical Properties

Appearance at 25°C	Clear solution
Solids, % by weight	68-72
Solvent	Ethanol/water
Color (APHA) - (50% solids solution in 1:1 alcohol:water)	100
Specific gravity, 25°C	~0.995
Viscosity, cps @ 25°C	
Brookfield RVE,	
No. 1 spindle 20 RPM	~100-150
Freezing point, °C	
30% solution ¹	-40 (40°F)
Flash Point, °C	
Pensky Marten (closed cup)	25 (77°F)
pH, 10% solids solution in 1:1 IPA:Water	5-7
Acid number, as is, max.	2.5
Iodine value, as is, max.	0.25
Solubility in water, g/100ml, 25°C	0.1 (but readily dispersible at higher conc.)
Solubility in organic solvents	very soluble

Biodegradability

AEROSOL TR-70 surfactant is biodegraded to 66% in 3 days when tested in the CSMA Shake Culture Test.

Electrolyte Tolerance

Because it is highly hydrophobic, AEROSOL TR-70 surfactant exhibits poor tolerance in electrolytes. In aqueous solutions, for example, AEROSOL TR-70 surfactant has a calcium tolerance of 31 ppm as CaCO₃ at 0.25% surfactant in water.

Stability

AEROSOL TR-70 surfactant will remain stable indefinitely under normal storage conditions. It should be stored above 25°F to avoid clouding. If evaporation of the solvent should occur, some of the AEROSOL TR-70 surfactant may crystallize out. The crystals can be redissolved by heating or by the

addition of alcohol or another organic solvent. Both aqueous and organic solvent solutions of AEROSOL TR-70 surfactants are stable up to temperatures of 100°C to 140°C. Above 150°C, AEROSOL TR-70 surfactant will decompose slowly on prolonged heating. In the presence of a strong acid or alkali at elevated temperatures, AEROSOL TR-70 surfactant is slowly hydrolyzed.

Health And Safety Information

Before handling this material, read the corresponding Cytec Industries Inc. Material Safety Data Sheet (#0051) for safety, health and environmental data. On the basis of toxicity tests, AEROSOL TR-70 surfactant is not expected to present any significant hazards to health in ordinary industrial handling. AEROSOL TR-70 surfactant is not phytotoxic if used in spray solutions at concentrations below 0.5%.

Storage And Handling

AEROSOL TR-70 surfactant is a Class I flammable liquid. Adequate precautions should be followed for this classification.

AEROSOL TR-70 surfactant may be stored and used in a wide variety of containers or reaction vessels. Stainless steel, aluminum and Monel alloy are recommended for reaction and storage vessels; glass, PE, PP and rubber are suitable lining materials. AEROSOL TR-70 surfactant itself is not corrosive.

Regulatory Information

This product is manufactured in compliance with all provisions of the Toxic Substance Control Act, 15. U.S.C. (TSCA).

All components of this product are included on the European Inventory of Existing Chemical Substances (EINECS), the Australian Inventory of Chemical Substances (AICS), the Japan Inventory (ENCS), the Korea Inventory (ECL), and the Philippines (PICS) Inventory.

• Email: custinfo@cytec.com Worldwide Contact Info: www.cytec.com US Toll Free 800-652-6013 Tel 973-357-3193 •

Cytec Industries Inc. in its own name and on behalf of its affiliated companies (collectively, "Cytec") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Cytec's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Cytec is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted for any specific use. The user or purchaser should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the user.

© 2010 Cytec Industries Inc. All rights reserved.

TRADEMARK NOTICE: The © indicates a Registered Trademark in the United States and the ™ or * indicates a Trademark in the United States. The mark may also be registered, the subject of an application for registration or a trademark in other countries.

PRT-066-B-EN-WW-10B